

放射光メスバウア分光法を用いた高圧下における Fe-Si 合金の物性研究 Study of physical properties of Fe-Si alloy at high pressure using using synchrotron radiation Mossbauer spectroscopy

鈴木 那奈美^{1*}; 大谷 栄治¹; 平尾 直久²; 鎌田 誠司¹; 浜田 麻希³; 坂巻 竜也¹; 大石 泰生²; 増田 亮⁴; 三井 隆也⁵
SUZUKI, Nanami^{1*}; OHTANI, Eiji¹; HIRAO, Naohisa²; KAMADA, Seiji¹; HAMADA, Maki³; SAKAMAKI, Tatsuya¹; OHISHI, Yasuo²; MASUDA, Ryo⁴; MITSUI, Takaya⁵

¹ 東北大学大学院理学研究科地学専攻, ² 高輝度光科学研究センター, ³ 金沢大学理工研究域自然システム学系, ⁴ 京都大学原子炉実験所, ⁵ 日本原子力研究開発機構

¹Department of Earth and planetary materials science, Graduate School of Science, ²Japan Synchrotron Radiation Research Institute, Hyogo, 679-5198, Japan, ³School of Natural System, College of Science and Engineering, Kanazawa University, Kanazawa, 920-119, ⁴Research Reactor Institute, Kyoto University, Osaka, 590-0494, Japan, ⁵Japan Atomic Energy Agency, Hyogo, 679-5148, Japan

The Earth's core is divided into the liquid outer core and solid inner core based on seismological observations. The Earth's core has been geochemically and cosmochemically thought to be mainly composed of Fe. The density of the core is smaller than that of pure iron under the core conditions. Therefore, the core has been considered to contain light elements, such as H, S, Si, C, and O. Si is one of the most important light elements in the core. Although the phase relations and compression behaviors in the Fe-Si alloy have been studied at high pressure and temperature in order to investigate properties of the inner core, magnetic properties of the alloys have not been studied well. In order to clarify the relationship between the magnetic transition and the structural transition of the Fe-Si alloy, we made simultaneous measurements of X-ray diffraction and synchrotron Mössbauer spectroscopy of the Fe-Si alloy up to 40 GPa at room temperature.

The Fe-Si alloy used for the measurements has a composition of Fe_{0.95}Si_{0.05} enriched with ⁵⁷Fe. The starting material was synthesized by melting the mixture of ⁵⁷Fe and Fe-Si alloys under the Ar-H₂ atmosphere by laser heating. Mössbauer spectra and XRD patterns were obtained at the beamlines, BL10XU and BL11XU of SPring-8 up to 40 GPa at room temperature. Our Mössbauer data together with X-ray diffraction data revealed that the magnetic transition from magnetic to non-magnetic phase occurs at 18 GPa simultaneously with the bcc to hcp transition. The change in the sound velocity and compression behavior of the Fe-Si alloy has been reported associated with the structural transformation of the alloy from bcc to hcp. The present results imply that the change in these physical properties is caused not only by the structural change but also by the magnetic transition.