In-situ IR measurement in homogeneous nucleation process of alumina under μG environment

*Shinnosuke Ishizuka¹, Yuki Kimura¹, Tomoya Yamazaki¹, Itsuki Sakon², Yuko Inatomi³

1.Institute of Low Temperature Science, Hokkaido University, 2.Graduate School of Science, University of Tokyo, 3.Japan Aerospace Exploration Agency

Homogeneous nucleation process from vapor is characterized by the ratio between time scales for supersaturation increase and for source collision expressed as $\Lambda[1]$. Under the physical condition with the same Avalue, homogeneous nucleation process has been regarded to follow the same process. At the dust forming front around evolved stars, Avalue has been calculated to be $\sim 10^{3-5}$ from total pressure and velocity of stellar wind. In contrast, Avalue of $\sim 10^{0-2}$ is known for the gas evaporation method which is one of the simplest experimental methods to produce dust analogues via homogeneous nucleation [2, 3].

In-situ IR measurement during nucleation of nanoparticles in the gas evaporation method proved multi-step formation of metal oxide from vapor to crystalline via liquid droplet in our ground based experiment [4]. Using our advanced technique, we measured IR spectra of nucleating alumina and its evolution while nanoparticles are free-flying under μ G environment in which Aapproximates to the value at dust formation region. Specially designed experimental apparatus equipped with dispersive IR spectrometer was loaded to S-520-30 sounding rocket by which the apparatus carried to altitude of 312 km. We also performed ground based experiment combined with FT-IR. IR spectra of nucleating alumina measured in ground based experiment showed broad absorption extending >11 μ m. Formed nanoparticles were observed by TEM and identified to δ -alumina. In contrast, sharp absorption centered at 13 μ m was appeared in μ G experiment. This 13 μ m band is one of the most indicative features of corundum (α -alumina) sphere. Corundum is the most plausible candidate for the origin of unidentified 13 μ m feature which is often observed for oxygen rich AGB stars with low-mass loss rate [5, 6]. Polymorphic behavior of alumina in homogeneous nucleation process at different Awill be the key to understand astronomical dust formation.

[1] Yamamoto, T. & Hasegawa, H., 1977 Progress of Theoretical Physics, Vol. 58, No. 3, 816
[2] Kimura, Y., Miura, H., Tsukamoto, K., Li, C. et al., 2011, J. Cryst. Growth, 316, 196
[3] Kimura, Y., Tanaka, K. K., Miura, H. & Tsukamoto, K., 2012, Crystal Growth & Design, 12(6), 3278-3284.

[4] Ishizuka, S., Kimura, Y. & Sakon, I., 2015, The Astrophysical Journal, 803 (2), 88.
[5] Speck, A. K., Barlow, M. J., Sylvester, R. J. & Hofmeister, A. M., 2000, Astronomy and Astrophysics Supplement Series, 146(3), 437-464.

[6] Sloan, G. C., Kraemer, K. E., Goebel, J. H. & Price, S. D., 2003, The Astrophysical Journal, 594(1), 483.