

SMP056-02

会場:展示ホール7別室2

時間: 5月23日09:15-09:30

## 高圧下におけるNi-NiS系の融解関係

### Melting relationships of the Ni-NiS system under pressure and the stability field of the Ni<sub>3</sub>S

浦川 啓<sup>1\*</sup>, 松原良輔<sup>1</sup>, 桂智男<sup>2</sup>, 渡辺 了<sup>3</sup>, 亀卦川卓美<sup>4</sup>

Satoru Urakawa<sup>1\*</sup>, Ryosuke Matsubara<sup>1</sup>, Tomoo Katsura<sup>2</sup>, Tohru Watanabe<sup>3</sup>,  
Takumi Kikegawa<sup>4</sup>

<sup>1</sup>岡山大学自然科学研究科, <sup>2</sup>パイロイト大学, <sup>3</sup>富山大学理工学研究部, <sup>4</sup>高エネ研放射光施設

<sup>1</sup>Dept Earth Sci, Okayama Univ, <sup>2</sup>Univ of Bayreuth, <sup>3</sup>Dept Earth Sci, Toyama Univ, <sup>4</sup>PF, KEK

The planetary core consists of iron-nickel alloy and lightening elements, such as sulfur and silicon. Study of melting relations of iron alloys is of important to understand formation, evolution, and the present state of the planetary core. An addition of nickel to iron affects significantly the phase relations of iron alloys. It is, therefore, reasonable to investigate the phase relations of the Ni alloys under pressure. Here, we report the results of quenching experiments and synchrotron radiation experiments on the phase relations of the Ni-NiS system up to 10 GPa.

Melting relations of the Ni-NiS system at 10 GPa were studied by quenching method using a KAWAI type high pressure apparatus at Okayama University, and the phase relations of the Ni-NiS system were investigated by synchrotron based in-situ observation using the MAX80 system at Photon Factory, at the pressure range from 1 to 10 GPa.

At 10 GPa, the system Ni-NiS is a eutectic system with the intermediate compounds, the Ni<sub>3</sub>S and the Ni<sub>3</sub>S<sub>2</sub>. The Ni<sub>3</sub>S is a new phase and it is an isostructural with Fe<sub>3</sub>S which has a Fe<sub>3</sub>P-type structure with a tetragonal symmetry (space group I-4). The Ni<sub>3</sub>S is stabilized above 5 GPa and it melts incongruently into Ni and liquid. Although the stability field of the Fe<sub>3</sub>S is limited to the higher pressure than 18 GPa, solid solution of the Ni<sub>3</sub>S into the Fe<sub>3</sub>S might extends its stability field to the lower pressure. The eutectic temperature of the Ni-NiS system is lower than that of the Fe-S system by at least 500 K at this pressure range. Therefore the addition of Ni to the Fe-S system lowers significantly its melting temperature, which is consistent with the previous studies. Although the eutectic point of the Ni-NiS system gradually moves towards Ni-rich with pressure, its location is confined between Ni<sub>3</sub>S and Ni<sub>3</sub>S<sub>2</sub>. The eutectic point of the Fe-FeS system is rich in sulfur relative to the Ni-NiS system below 10 GPa, but it becomes sulfur less composition with pressure and locates the Fe-rich side of Fe<sub>3</sub>S above 20 GPa. Thus the addition of Ni can affects significantly not only the temperature but also the composition of the eutectic point of the Fe-FeS system. We will also discuss the physical properties of the Ni<sub>3</sub>S determined by synchrotron experiments.

キーワード:核,鉄合金の融解, Fe-FeS, Ni<sub>3</sub>S

Keywords: planetary core, melting of iron alloy, Fe-FeS, Ni<sub>3</sub>S