

SMP057-03

会場: 301A

時間: 5月23日14:11-14:24

## 合成 $\text{Ca}_2\text{Al}_3\text{-pMn}_3\text{+pSi}_3\text{O}_{12}(\text{OD})$ -紅簾石のX線・中性子結晶構造解析

### X-ray and neutron Rietveld refinement of $\text{Ca}_2\text{Al}_3\text{-pMn}_3\text{+pSi}_3\text{O}_{12}(\text{OD})$ -piemontite

赤坂 正秀<sup>1\*</sup>, 永嶋真理子<sup>2</sup>, 濱田麻希<sup>1</sup>, 佐野 亜沙美<sup>3</sup>, 江島輝美<sup>1</sup>

Masahide Akasaka<sup>1\*</sup>, Mariko Nagashima<sup>2</sup>, Maki Hamada<sup>1</sup>, Asami Sano<sup>3</sup>, Terumi Ejima<sup>1</sup>

<sup>1</sup>島根大学総合理工学部, <sup>2</sup>山口大学理学部, <sup>3</sup>日本原子力機構

<sup>1</sup>Shimane University, <sup>2</sup>Yamaguchi University, <sup>3</sup>Japan Atomic Energy Agency

Synthesis experiments of  $\text{Ca}_2\text{Al}_3\text{-pMn}_3\text{+pSi}_3\text{O}_{12}(\text{OD})$ -piemontite were performed for the crystal structure analysis and determination of hydrogen positions in epidote structure. The starting materials (S.M.) of oxide mixture with stoichiometric compositions ( $p = 0.5, 0.75, 1.0$  and  $1.1$ ) and  $\text{D}_2\text{O}$  were used for hydrothermal synthesis experiments at  $0.3$  GPa and  $500$  °C. In this study, almost single phase piemontite was synthesized by the run using S.M. with  $p = 1.0$ . X-ray data were obtained using conventional X-ray powder diffractometer, and the neutron diffraction data of the piemontite were measured using JRR3-HRPD. The unit-cell parameters given by the X-ray data are  $a$  8.8450(5),  $b$  5.6676(2),  $c$  10.1472(7) Å, and  $\beta$  115.495(4)°, and the site occupancies at M1 and M3 of  $\text{Al}_{0.63}\text{Mn}_{0.37}$  and  $\text{Al}_{0.36}\text{Mn}_{0.63}$ , respectively. On the other hand, the unit-cell parameters of  $a$  8.853(1),  $b$  5.6753(4),  $c$  10.159(2) Å, and  $\beta$  115.49(1)°, and the site occupancies at M1 and M3 of  $\text{Al}_{0.85}\text{Mn}_{0.15}$  and  $\text{Al}_{0.15}\text{Mn}_{0.85}$ , respectively, were given using a neutron diffraction data. The D position was determined successfully without any constraint.

キーワード: 重水素, 紅簾石, 合成, 中性子回折, X線回折, リートベルト解析

Keywords: Deuterium, Piemontite, Synthesis, Neutron diffraction, X-ray diffraction, Rietveld analysis