

SRD051-03

会場:ファンクショナルルームA

時間: 5月23日16:00-16:15

## 豪州・ノーランズボア鉱床産鉱石と燐灰石のREE組成

### REE contents of ore and apatite from Nolans Bore REE-P-U deposit, Australia: Implication for REE mineralization

村上 浩康<sup>1\*</sup>, 佐藤比奈子<sup>3</sup>, 石山大三<sup>3</sup>, 昆 慶明<sup>1</sup>, 石原 舜三<sup>2</sup>

Hiroyasu Murakami<sup>1\*</sup>, Hinako Sato<sup>3</sup>, Daizo Ishiyama<sup>3</sup>, Yoshiaki Kon<sup>1</sup>, Shunso Ishihara<sup>2</sup>

<sup>1</sup>産業技術総合研究所地圏資源環境研究部門, <sup>2</sup>産業技術総合研究所, <sup>3</sup>秋田大学工学資源学部

<sup>1</sup>Inst Geo-Resources and Environment, AIST, <sup>2</sup>Geological Survey of Japan, AIST,

<sup>3</sup>Eng. and Resour. Sci., Akita Univ.

Nolans Bore REE-P-U deposit, Northern Territory, Australia, is one of the most promising REE resources in the world. High grade REE ore derived from Nolans Bore deposit consists mainly of apatite with various amounts of acid-resistant minerals such as monazite-group mineral. Here we report that REE content of ore and apatite was analyzed by ICP-MS and LA-ICP-MS, respectively. In the analysis for ore by ICP-MS, we applied two different preparation methods before the analysis; Li-borate-fusion in a commercial laboratory and multi-acid digestion. Result derived from multi-acid digestion method is likely to be a true value relative to the other method. The high-grade REE ore is enriched in light-REE, especially Ce and Nd, with a maximum value of around 7 wt % total REE. The quantitative analysis by multi-acid digestion is highly precise and reliable for a wide range of REE concentration when using suitable dilution ratio and digestion sequence with several types of acids which could totally dissolve acid-resistant minerals such as monazite. On the other hand, analysis by Li-borate-fusion potentially gives lower trace element values than that of multi-acid digestion, when a sample is extremely concentrated in trace elements including REE. Apatite occurs as veins varying its width up to several tens meters wide. Petrographic studies indicate that there are two major types of apatite. Type 1 apatite occurs as euhedral grains containing fine-grained inclusions (hematite or multiple-oxide?) which exhibits an amoeba-like texture. Type 1 apatite is dominant in the ore. Type 2 apatite is sporadically present and occurs as anhedral and along grain-boundary. Fragments of type 1 apatite grains are sporadically present in the type 2; suggesting that type 1 was formed earlier than type 2, which is considered supergene in origin. Type 1 apatite has a bright CL-image, but type 2 has no luminescence. LA-ICP-MS analysis reveals that type 1 apatite is extremely enriched in REE together with Th and U contents. On the contrary, type 2 apatite is almost pure fluoro-apatite and is free of REE, Th and U. The type 1 apatite has high content of Ce and Nd, with a maximum value around 6 wt % total REE. The REE composition in type 1 apatite resembles that of ore; implying the type 1 apatite, relative to acid-resistant minerals, principally contributes the REE grade of the ore deposit.

キーワード:希土類元素,燐灰石,ノーランズボア鉱床,レーザーアブレイションICP-MS

Keywords: REE, apatite, Nolans Bore deposit, LA-ICP-MS