Japan Geoscience Union Meeting 2012

(May 20-25 2012 at Makuhari, Chiba, Japan)

©2012. Japan Geoscience Union. All Rights Reserved.



会場:102B



時間:5月22日11:15-11:30

Ca2MgSi2O7-Ca2Fe3+AlSIO7系合成メリライトの二つの四配位席における陽イオン 分布と変調構造の関係について

Distribution of cations at two tetrahedral sites in Ca2MgSi2O7-Ca2Fe3+AlSiO7 series synthetic melilite and its relation

浜田 麻希 ¹*, 赤坂 正秀 ¹ HAMADA, Maki¹*, AKASAKA, Masahide¹

¹ 島根大 総合理工 ¹Shimane Univ.

Synthetic melilites, $W_2T1T2_2O_7$, were analyzed to determine the distribution of Fe^{3+} between two different tetrahedral sites (T1 and T2), and the relationship between ionic substitution and incommensurate structure in melilite. Melilites on the join $Ca_2MgSi_2O_7$ ("<a>kermanite: Ak)- $Ca_2Fe^{3+}AlSiO_7$ (ferrialuminium gehlenite: FAGeh) system were synthesized from starting materials with compositions of Ak_{100} (100Ak), $Ak_{80}FAGeh_{20}$ (80Ak), $Ak_{70}FAGeh_{30}$ (70Ak) and $Ak_{50}FAGeh_{50}$ (by sintering at 1200-1250 "<o>C and 1 atm. The synthetic melilites were analyzed using X-ray powder diffraction, ⁵⁷Fe Mossbauer, and high-resolution transmission electron microscopic methods. The average chemical compositions and end-member components, Ak, FAGeh and Geh ($Ca_2Al_2SiO_7$), of the synthetic melilites were $Ca_{2.015}Mg_{1.023}Si_{1.981}O_7$ (100Ak), $Ca_{2.017}Mg_{0.788}Fe^{3+}_{0.187}Al_{0.221}Si_{1.791}O$ (80Ak), $Ca_{1.995}Mg_{0.695}Fe^{3+}_{0.258}Al_{0.318}Si_{1.723}O_7$ (70Ak) and $Ca_{1.982}Mg_{0.495}Fe^{3+}_{0.449}Al_{0.519}Si_{1.535}O_7$ (50Ak), respectively. The site populations at the T1 and T2 sites were [0.788Mg+0.054Fe^{3+}+0.158Al]T1[0.056Fe^{3+}+0.153Al+1.791Si]T2 for

The site populations at the T1 and T2 sites were $[0.788Mg+0.054Fe^{3+}+0.158Al]T1[0.056Fe^{3+}+0.153Al+1.791Si]T2$ for 80Ak, $[0.695Mg+0.105Fe^{3+}+0.200Al]T1[0.112Fe^{3+}+0.165Al+1.723Si]T2$ for 70Ak and $[0.495Mg+0.173Fe^{3+}+0.332Al]T1[0.281Fe^{3+}+10.50Ak$ (apfu: atoms per formula unit), respectively. The results indicate that Fe³⁺ is distributed at both the T1 and the T2 sites. The mean T1-O distance decreases with the substitution of Fe³⁺+Al³⁺ for Mg²⁺ at the T1 site, whereas the mean T2-O distance increases with substitution of Fe³⁺+Al³⁺ for Si⁴⁺ at the T2 site, causing decrease in the *a* dimension and increase of the *c* dimension.

The existence of incommensurate structure in all synthetic melilites at room temperature was confirmed by Mossbauer and CuK_{alpha1} X-ray line profile analyses. The Mossbauer spectra of the melilites consist of two doublets assigned to Fe³⁺ at the T1 site and two or three doublets to Fe³⁺ at the T2 site, which imply the existence of multiple T1 and T2 sites with different site distortions, respectively. The existence of two T1 sites is not influenced by ionic substitution. Conversely, the splitting of T2 sites becomes more remarkable with the substitution of Fe³⁺ +Al³⁺ for Si⁴⁺ which results in the increase of volume and site distortion of the T2O₄-tetrahedra.

Incommensurate structure in melilite has been interpreted rather statically, based on the crystal structure of " $\{a\}$ kermanite, that the incommensurate structure is caused by the misfit between the tetrahedral sheet and the polyhedral sheet However, as found in this study, effect of ionic substitution at the T1 and T2 sites on the formation of incommensurate structure is also significant. The first factor is the site distortion arising from the distribution of cations with different ionic radii in the T1 and T2 sites. Even though the cation sites are symmetrically equivalent in the average structure, each tetrahedron which is occupied by different cation(s) has variant volume. The second factor is the site distortions caused by the difference of adjacent coordination polyhedra around tetrahedra. Therefore, in Ak-FAGeh melilite solid solutions, the site distortions caused by the ionic substitution at the tetrahedral sites play important role on the formation of the incommensurate structure.

キーワード: 合成メリライト, 変調構造, 粉末 X線回折, 電子線回折, メスバウアー分光分析

Keywords: synthetic melilite, incommensurate structure, X-ray powder diffraction method, Electron diffraction, Mossbauer spectroscopy