

レーザー衝撃圧縮した FeSi の音速密度測定 Sound velocity and density measurements of FeSi alloy by laser-shock compression

細木 亮太^{1*}, 横山 直也¹, 境家 達弘¹, 近藤 忠¹, 寺崎 英紀¹, 弘中 陽一郎², 重森 啓介²

Ryota Hosogi^{1*}, Naoya Yokoyama¹, Tatsuhiko Sakaiya¹, Tadashi Kondo¹, Hidenori Terasaki¹, Yoichiro Hironaka², Keisuke Shigemori²

¹ 大阪大学大学院理学研究科宇宙地球科学専攻, ² 大阪大学レーザーエネルギー学研究センター

¹Graduate School of Science, Osaka University, ²Institute of Laser Engineering, Osaka University

It is well known that Earth's core consists of mainly iron (Fe) alloyed with a few percent of light elements. Several light elements (hydrogen, carbon, oxygen, silicon, sulfur, etc.) have been considered as the candidate of the composition of Earth's core, but its composition is still unclear. In order to constrain the core composition, it is important to measure the sound velocity of iron alloys because it can be directly compared with the seismic wave. Silicon (Si) has been proposed as a major light element in the inner core [Mao et al., 2012]. So we measured the sound velocity of laser-shocked FeSi alloy in order to investigate the effect of Si for sound velocity of liquid Fe in the outer core.

The starting sample was prepared by synthesizing from mixture of Fe (99.98% purity) and Si (99.9% purity) slugs at arc furnace. The compositions of Fe and Si are 66.5 wt.% and 33.5 wt.%, respectively. We measured sound velocities and densities of FeSi at high pressure and high temperature conditions at the large laser facility in Institute of Laser Engineering, Osaka University. The sound velocities were measured by the x-ray radiography [Shigemori et al., 2012].

We obtained the sound velocity and density of FeSi at pressures around 700 GPa. It is seen that Si has the effect of increasing the sound velocity of liquid Fe. Comparing our experimental results and PREM model [Dziewonski and Anderson, 1981], Si may be contained up to 17 wt.% at 135 GPa, and up to 6.4 wt.% at 330 GPa in the outer core.

キーワード: レーザー, 音速, 外核, FeSi

Keywords: laser, sound velocity, outer core, FeSi