

高温高圧下における Fe-Ni-C の音速測定 Sound velocity of liquid Fe-Ni-C alloy at high pressure and temperature

桑原 荘馬^{1*}, 西田 圭佑², 寺崎 英紀¹, 舟越 賢一³, 肥後 祐司³, 潮田 雅司², 櫻井 萌², 近藤 忠¹
Souma Kuwabara^{1*}, Keisuke Nishida², Hidenori Terasaki¹, Ken-ichi Funakoshi³, Yuji Higo³, Masashi Ushioda², Moe Sakurai²,
Tadashi Kondo¹

¹ 大阪大学理学研究科宇宙地球科学専攻, ² 東京工業大学地球惑星科学専攻地球惑星科学科, ³ 独立行政法人日本原子力研究開発機構

¹Graduate School of Science, Osaka University, ²Graduate School of Science and Engineering, Tokyo Institute of Technology,

³Japan Atomic Energy Agency

Sound velocity is important to understand the composition of the Earth's and lunar core because it can be directly compared with seismological data.

Carbon is a plausible candidate as a light element in the core due to its high cosmic abundance and high affinity to liquid Fe [e.g., Wood, 1993]. However, the effect of carbon on the sound velocity (V_P) of liquid Fe-Ni alloy has not been investigated. In this study, we have measured the V_P of liquid (Fe-10wt.%Ni)-4wt.%C alloy at around 4.7 GPa and 1563-1788 K.

High-pressure experiment was performed using a 1500-ton multi-anvil apparatus (SPEED-1500) installed at BL04B1 of the SPring-8 synchrotron radiation facility. Experimental pressure was determined from the lattice constants of MgO and hBN. We have used a cylindrical graphite heater and temperature was monitored using a W5%Re-W26%Re thermocouple. V_P measurements were carried out by the pulse-echo-overlap method using a LiNbO₃ transducer for generating and receiving P-wave signals. Used frequencies of the wave signal were 37 and 21 MHz. The sample length was measured from an X-ray radiography image of the sample.

The observed V_P of liquid Fe-Ni-C decreases with increasing temperature. Comparing the V_P of Fe-C calculated from the previously reported densities and bulk moduli of liquid Fe and Fe-C [Anderson & Ahrens, 1994; Shimoyama et al., 2013; Terasaki et al., 2010], V_P of liquid Fe-C or Fe-Ni-C decrease with increasing carbon content.

キーワード: 炭素, 地球外核, 軽元素

Keywords: Carbon, Earth's outer core, Light element