

## 単結晶モナザイトの水熱合成及びモナザイトに対する水の溶解度測定 The structural water in hydrothermally synthesized monazite

阿部 健康<sup>1\*</sup>; 中村 美千彦<sup>1</sup>  
ABE, Takeyasu<sup>1\*</sup>; NAKAMURA, Michihiko<sup>1</sup>

<sup>1</sup> 東北大学理学研究科地学専攻

<sup>1</sup>Department of Earth Sciences, Tohoku University

**Introduction:** The U-Th-Pb dating of accessory minerals such as zircon and monazite is widely applied for various types of rocks [1,2,3]. There has been proposed another method to obtain geochronological information from these minerals: quantifying the degree of metamictization (destruction of crystal structure by radioactive components). It is reported for zircon that the water content (up to 10 wt%) is in proportion to the degree of metamictization, thus to the concentration of radioactive nuclei and geological age[4]. Monazite on the other hand usually undergoes much less metamictization than zircon due to the higher bond strength of P and O compared to that of Si and O; this results in the lower water content in the metamictized monazite. Determination of the structural water content in monazite without radioactive damage is thus necessary to constrain the "initial" water content prior to hydration. The water content bears significance also for better understanding the crystal chemistry of monazite. In this study, we synthesized monazite single crystals at hydrothermal condition and determined the content of structural water as a function of pressure.

**Experimental method:** The hydrothermal synthesis of monazite was conducted at a temperature of 800 degC and pressures of 1.5, 10 and 15 kbar using a cold-seal pressure vessel and a piston cylinder apparatus. The CePO<sub>4</sub> reagent was encapsulated with H<sub>2</sub>O or H<sub>2</sub>O-NaCl solution and run for ca. 100 hours. The FT-IR analyses of the obtained monazite single crystals were conducted to determine the concentration of structural OH on the basis of Lambert-Beer's Law. The molar absorption coefficient was estimated by linear calibration curve against the OH stretching vibration wavenumber [5].

**Results and Discussion:** The broad absorption band was observed at 3100-3600 cm<sup>-1</sup> in the crystals synthesized in all the experimental conditions. The water content of synthesized monazite was estimated approximately to be 20-70 ppm, showing no large pressure dependence. FT-IR analyses of pleochroic absorption are on-going to determine the OH dipole orientation within the crystal structure.

**References:** [1]J. M. Langille, M. J. Jessup, J. M. Cottle, G. Lederer, T. Ahmad, *Journal of Metamorphic Geology*, 30, 769-791 (2012)

[2]E. Janots, A. Berger, E. Gnos, M. Whitehouse, E. Lewin, T. Pettke, *Chemical Geology*, 326-327, 61-71 (2012)

[3]T. Imayama, K. Suzuki, *American Mineralogist*, 98, 1393-1406 (2013)

[4]M. Zhang, E. K. H. Salje, R. C. Ewing, *Journal of Physics: Condensed Matter*, 14, 3333-3352 (2002)

[5]M. S. Paterson, *Bulletin de Mineralogie*, 105, 20-29 (1982)

キーワード: 水熱合成, アクセサリー鉱物, モナザイト年代, メタミクト化, NAMs, フーリエ変換型赤外分光装置

Keywords: hydrothermal synthesis, accessory mineral, monazite dating, metamictization, nominally anhydrous minerals, FT-IR